

This listing of claims will replace all prior versions, and listings, or claims in the application.

**Listing of the Claims:**

Claims 1-10 (cancelled)

11. (Currently amended) A method for the preparation of a cross-linked hydrophilic coating of a hydrophilic polymer on a substrate polymer surface of a medical device, said method consisting essentially of ~~comprising~~ the steps of:

(i) providing a medical device having a substrate polymer surface;

(ii) providing a polymer solution comprising 1-20% by weight of a hydrophilic polymer, 0-5% by weight of additive(s), and the balance of said solution is comprised of a vehicle having at least one plasticizer with a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen  $\delta_H$  parameter of less than 20;

(iii) applying said polymer solution to said substrate polymer surface;

(iv) evaporating at least a part of the vehicle from said

polymer solution present on said substrate polymer surface; and

(v) curing said hydrophilic polymer, wherein said curing is the only irradiation step in the process.

12. (Previously presented) The method according to claim 11, wherein the polymer solution is applied to said substrate polymer surface in one single application step.

13. (Previously presented) The method according to claim 11, wherein the vehicle comprises at least one solvent.

14. (Previously presented) The method according to claim 13, wherein the polymer solution consists of 1-20% by weight of the hydrophilic polymer, 0-5% by weight of additive(s), 1-40% by weight of plasticizer(s), and 50-95% by weight of solvent(s).

15. (Previously presented) The method according to claim 11, wherein the substrate polymer is polyurethane.

16. (Previously presented) The method according to claim 11, wherein the hydrophilic polymer is polyvinyl pyrrolidone.

17. (Previously presented) A medical device comprising a substrate polymer surface having thereon a cross-linked hydrophilic coating of a hydrophilic polymer, said medical device being obtained by the method of claim 11.

18. (Previously presented) A medical device comprising a hydrophilic coating of a cross-linked hydrophilic polymer, said coating comprising a hydrophilic plasticizer having a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen  $\delta_H$  parameter of less than 20.

19. (Previously presented) A medical device comprising a hydrophilic coating of a cross-linked hydrophilic polymer, said coating having a hydrophilic plasticizer with a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen  $\delta_H$  parameter of less than 20, said medical device being prepared according to the method of claim 11.

20. (Previously presented) The method of use of a polymer solution for the preparation of a cross-linked hydrophilic coating, wherein said polymer solution includes 1-20% by weight of a hydrophilic polymer, 0-5% by weight of additive(s), and the

balance of said solution is a vehicle having a plasticizing effect on the hydrophilic polymer and including at least one plasticizer having a solubility in water of at least 6 g/L, a boiling point above 210°C at 760 mmHg, and a Hansen  $\delta_H$  parameter of less than 20, said method consisting essentially of ~~including~~ the steps of:

(a) applying said polymer solution to said substrate polymer surface;

(b) evaporating at least a part of the vehicle from said polymer solution present on said substrate polymer surface; and curing said hydrophilic polymer,

wherein said method includes only a single irradiation step.

21. (Previously presented) The method according to claim 15, wherein the hydrophilic polymer is polyvinyl pyrrolidone.